

IB Series I-Joists International Beams, Inc.

PR-L252
Revised July 27, 2010

Products: IB-400, 600, 800 and 900 Prefabricated Wood I-Joists
International Beams, Inc., 480, rue Jocelyn-Bastille, CP 10, Pohénégamook, Quebec, Canada.
www.internationalbeams.com

1. Basis of the product report:
 - 2006 and 2009 International Building Code (IBC): Sections 104.11 Alternative Materials and 2303.1.2 Prefabricated wood I-joists
 - 2006 and 2009 International Residential Code (IRC): Sections R104.11 Alternative Materials and R502.1.4 Prefabricated wood I-joists
 - ASTM D 5055-05 recognized by the 2009 IBC and IRC
 - Performance Standard for APA EWS I-Joists, PRI-400
 - APA Reports T2000P-42A, T2001P-53, T2001P-63, T2001P-78, T2002P-65, T2003P-17, T2003P-18A, T2003P-52, T2005P-01A, T2005P-40B, T2005P-99A, T2006P-36, T2006P-43, T2006P-53, T2008P-37, T2009P-34A, T2010P-06, and other qualification data
2. Product description:

IB Series I-joists are made with lumber flanges and OSB web in accordance with the in-plant manufacturing standard approved by APA.
3. Design properties:

Tables 1 through 3 list the design properties for IB Series I-joists. The allowable spans for IB Series I-joists shall be in accordance with the recommendations provided by the manufacturer (www.internationalbeams.com), and with APA Design & Construction Guide, *Performance Rated I-Joists*, Form Z725 (www.apawood.org/publications) for products contained in the PRI Series.
4. Product installation:

IB Series I-joists shall be installed in accordance with the recommendations provided by the manufacturer (see link above) and APA Design & Construction Guide, *I-Joist Construction Details*, Form D710 (see link above). Permissible web holes and cantilever reinforcements shall be in accordance with the recommendations provided by the manufacturer, and with APA D710 for products contained in the PRI Series.
5. Fire-rated assemblies:

Fire-rated assemblies shall be constructed in accordance with the recommendations provided by the manufacturer (see link above), and with APA Design & Construction Guide, *Fire-Rated Systems*, Form W305 (see link above) for products contained in the PRI Series.
6. Limitations:
 - a) IB Series I-joists shall be designed in accordance with the code using the design properties specified in this report.
 - b) IB Series I-joists are limited to dry service conditions where the average moisture content of lumber is less than 16 percent.
 - c) IB Series I-joists are produced at International Beams' facility in Pohénégamook, Quebec, under a quality assurance program audited by APA.
 - d) This report is subject to re-examination in one year.
7. Identification:

The IB prefabricated wood I-joists described in this report are identified by a label bearing the manufacturer's name (International Beams) and/or trademark, the APA assigned plant number of 1033 for the Pohénégamook plant, the I-joist depth and series, the APA logo, the report number PR-L252, and a means of identifying the date of manufacture.

Table 1. Design Properties (Allowable Stress Design) for IB Series I-Joists ^(a)

Joist Designation	Also Qualified for	EI ^(b) (10 ⁶ lbf-in. ²)	M ^(c) (lbf-ft)	V ^(d) (lbf)		Vertical load (plf)	K ^(g) (10 ⁶ lbf)
				Without bearing stiffeners	With bearing stiffeners		
9-1/4" IB-400	NA	185	2,715	1,155	1,155	2,000	4.81
9-1/2" IB-400	9-1/2" PRI-40	198	2,800	1,185	1,185	2,000	4.94
11-1/4" IB-400	NA	296	3,410	1,405	1,405	2,000	5.85
11-7/8" IB-400	11-7/8" PRI-40	336	3,630	1,480	1,480	2,000	6.18
14" IB-400	14" PRI-40	494	4,370	1,550	1,750	2,000	7.28
16" IB-400	16" PRI-40	673	5,065	1,550	2,000	2,000	8.32
9-1/4" IB-600	NA	220	3,740	1,155	1,350	2,000	4.81
9-1/2" IB-600	9-1/2" PRI-60	235	3,860	1,185	1,370	2,000	4.94
11-1/4" IB-600	NA	356	4,700	1,405	1,515	2,000	5.85
11-7/8" IB-600	11-7/8" PRI-60	399	5,000	1,480	1,570	2,000	6.18
14" IB-600	14" PRI-60	585	6,020	1,550	1,750	2,000	7.28
16" IB-600	16" PRI-60	799	6,980	1,550	2,000	2,000	8.32
18" IB-600	NA	1,046	7,895	1,550	2,250	1,750	9.36
20" IB-600	NA	1,304	8,735	1,550	2,500	1,500	10.40
9-1/4" IB-800	NA	307	5,295	1,155	1,390	2,000	4.81
9-1/2" IB-800	9-1/2" PRI-80	326	5,465	1,185	1,405	2,000	4.94
11-1/4" IB-800	NA	493	6,655	1,405	1,540	2,000	5.85
11-7/8" IB-800	11-7/8" PRI-80	552	7,080	1,480	1,585	2,000	6.18
14" IB-800	14" PRI-80	807	8,530	1,550	1,750	2,000	7.28
16" IB-800	16" PRI-80	1,094	9,890	1,550	2,000	2,000	8.32
18" IB-800	NA	1,445	11,135	1,600	2,300	1,810	9.36
20" IB-800	NA	1,799	12,380	1,650	2,600	1,625	10.40
11-7/8" IB-900	11-7/8" PRI-90	604	8,825	1,885	1,925	2,000	6.18
14" IB-900	14" PRI-90	884	10,630	1,885	2,125	2,000	7.28
16" IB-900	16" PRI-90	1,199	12,635	1,885	2,330	2,000	8.32
18" IB-900	NA	1,565	14,285	1,885	2,510	1,810	11.52
20" IB-900	NA	1,984	15,810	1,885	2,695	1,625	12.80
22" IB-900	NA	2,457	17,320	1,885	2,875	1,250	14.08
24" IB-900	NA	2,985	18,810	1,885	3,060	1,250	15.36

(a) The tabulated values are design values for normal duration of load. All values, except for EI and K, shall be permitted to be adjusted for other load durations as permitted by the code. Values for Limit States Design in Canada are available from the manufacturer.

(b) Bending stiffness (EI) of the I-joist.

(c) Moment capacity (M) of the I-joist, which shall not be increased by any repetitive member use factor.

(d) Shear capacity (V) of the I-joist with a minimum end bearing length of 4"

(e) Coefficient of shear deflection (K). For calculating uniform load and center-point load deflections of the I-joist in a simple-span application, use Eqs. 1 and 2.

$$\text{Uniform Load: } \delta = \frac{5\omega\ell^4}{384EI} + \frac{\omega\ell^2}{K} \quad [1]$$

$$\text{Center-Point Load: } \delta = \frac{P\ell^3}{48EI} + \frac{2P\ell}{K} \quad [2]$$

Where: δ = calculated deflection (in.), ω = uniform load (lbf/in.),
 P = concentrated load (lbf), ℓ = design span (in.),
 EI = bending stiffness of the I-joist (lbf-in.²), and
 K = coefficient of shear deflection (lbf).

Table 2. Intermediate Reaction Design Properties (Allowable Stress Design) for IB Series I-Joists^(a)

Joist Designation	Joist Depth	Also Qualified for	IR (Ibf)			
			3-1/2-in. Bearing		5-1/2-in. Bearing	
			w/o BS	w/ BS	w/o BS	w/ BS
IB-400	9-1/4"	NA	2,160	2,310	2,310	2,310
	9-1/2"	9-1/2" PRI-40	2,160	2,370	2,370	2,370
	11-1/4"	NA	2,500	2,795	2,810	2,810
	11-7/8"	11-7/8" PRI-40	2,500	2,795	2,810	2,960
	14"	14" PRI-40	2,500	2,795	3,100	3,455
	16"	16" PRI-40	2,500	2,795	3,100	3,650
IB-600	9-1/4"	NA	2,160	2,700	2,310	2,700
	9-1/2"	9-1/2" PRI-60	2,160	2,740	2,370	2,740
	11-1/4"	NA	2,500	3,030	2,810	3,030
	11-7/8"	11-7/8" PRI-60	2,500	3,075	2,810	3,140
	14"	14" PRI-60	2,500	3,215	3,100	3,455
	16"	16" PRI-60	2,500	3,350	3,100	3,650
	18"	NA	2,500	3,425	3,100	3,735
20"	NA	2,500	3,450	3,100	3,820	
IB-800	9-1/4"	NA	2,310	2,700	2,310	2,700
	9-1/2"	NA	2,370	2,740	2,370	2,740
	11-1/4"	NA	2,810	3,030	2,810	3,030
	11-7/8"	11-7/8" PRI-80	2,810	3,140	2,810	3,140
	14"	14" PRI-80	3,020	3,500	3,100	3,500
	16"	16" PRI-80	3,100	4,000	3,100	4,000
	18"	NA	3,100	4,225	3,100	4,225
20"	NA	3,100	4,350	3,100	4,350	
IB-900	11-7/8"	11-7/8" PRI-90	3,355	3,355	3,355	3,355
	14"	14" PRI-90	3,355	3,530	3,355	3,660
	16"	16" PRI-90	3,355	3,920	3,355	4,090
	18"	NA	3,355	4,270	3,355	4,640
	20"	NA	3,355	4,600	3,355	5,000
	22"	NA	3,355	4,950	3,355	5,075
	24"	NA	3,355	5,150	3,355	5,150

^(a) Interpolation between 3-1/2- and 5-1/2-inch IR shall be permitted.

Table 3. End Reaction Design Properties (Allowable Stress Design) for IB Series I-Joists ^(a)

Joist Designation	Joist Depth	Also Qualified for	ER (lbf)			
			1-3/4-in. Bearing		3-1/2-in. Bearing	
			w/o BS	w/ BS	w/o BS	w/ BS
IB-400	9-1/4"	NA	1,080	1,080	1,135	1,135
	9-1/2"	9-1/2" PRI-40	1,080	1,080	1,160	1,160
	11-1/4"	NA	1,200	1,200	1,355	1,355
	11-7/8"	11-7/8" PRI-40	1,200	1,200	1,415	1,415
	14"	14" PRI-40	1,200	1,200	1,550	1,550
	16"	16" PRI-40	1,200	1,200	1,550	1,550
IB-600	9-1/4"	NA	1,080	1,350	1,135	1,350
	9-1/2"	9-1/2" PRI-60	1,080	1,370	1,160	1,370
	11-1/4"	NA	1,200	1,515	1,355	1,515
	11-7/8"	11-7/8" PRI-60	1,200	1,570	1,415	1,570
	14"	14" PRI-60	1,290	1,725	1,550	1,750
	16"	16" PRI-60	1,375	1,725	1,550	2,000
	20"	NA	1,550	1,725	1,550	2,500
IB-800	9-1/4"	NA	1,080	1,380	1,135	1,380
	9-1/2"	NA	1,080	1,405	1,160	1,405
	11-1/4"	NA	1,200	1,540	1,355	1,540
	11-7/8"	11-7/8" PRI-80	1,280	1,585	1,415	1,585
	14"	14" PRI-80	1,290	1,750	1,550	1,750
	16"	16" PRI-80	1,375	2,000	1,550	2,000
	18"	NA	1,465	2,270	1,550	2,300
	20"	NA	1,550	2,460	1,550	2,600
IB-900	11-7/8"	11-7/8" PRI-90	1,400	1,585	1,805	1,805
	14"	14" PRI-90	1,400	1,750	1,805	1,960
	16"	16" PRI-90	1,400	2,000	1,805	2,330
	18"	NA	1,465	2,270	1,675	2,510
	20"	NA	1,550	2,470	1,675	2,680
	24"	NA	1,470	2,880	1,675	2,960

^(a) For an end reaction bearing length of 4 inches or longer, the end reaction shall be permitted to be set equal to the tabulated shear value. Interpolation of the end reaction between tabulated bearing lengths shall be permitted.

APA – *The Engineered Wood Association* is an accredited certification body under ISO 65 by Standards Council of Canada (SCC) and an accredited inspection agency by the International Code Council (ICC) International Accreditation Service (IAS) under ISO/IEC 17020. APA is also an accredited testing organization recognized by IAS and SCC under ISO/IEC 17025. APA is a recognized testing laboratory by Miami-Dade County, and a Product Testing Laboratory, Product Quality Assurance Entity, and Product Validation Entity by the Florida Department of Community Affairs (DCA).

**APA – THE ENGINEERED WOOD ASSOCIATION
HEADQUARTERS**

7011 So. 19th St. • Tacoma, Washington 98466
Phone: (253) 565-6600 • Fax: (253) 565-7265 • Internet Address: www.apawood.org

PRODUCT SUPPORT HELP DESK
(253) 620-7400 • E-mail Address: help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of APA – *The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility of product performance or designs as actually constructed.